

HEXATAN SMRP

Powdered Acrylic maleic polymer

Suitable articles

Suitable for all kinds of leather

Highlights

Poly acrylic maleic resin in powder form. Very much suitable for using in all stages of leather processing

The product is free from RSL chemicals (Restricted substances list) such as formaldehyde.

HEXATAN SMRP

- **HEXATAN SMRP** maintain inner softness even after wet toggling and nailing, so it is best suitable for Upholstery leather
- **HEXATAN SMRP** is especially suitable for filling loose fibres in upper leather.
- **HEXATAN SMRP** imparts in leather fullness, grain smoothness and improves the thickness.
- Due to its excellent light fastness **HEXATAN SMRP** is best suitable for white leathers and pastel shades.
- **HEXATAN SMRP** is not compatible with mineral tanning agents.
- **HEXATAN SMRP** when used in re-tanning of chrome tanned leather, it improves the fullness and tightness of grain with elastic and bouncing properties.

PROPERTIES

Aspect	: Off white powder
Basis	: Maleic – acrylic copolymer
pH (1:10)	: 7.5 - 9.0
Solubility	: Good
Light fastness	: Excellent
Stability	: Stable at all pH values

APPLICATIONS

Re-tanning: In re-tanning **HEXATAN SMRP** can be applied after neutralization in the same bath, before addition of other re-tanning agents. It can also be added before or after fat liquoring.

Softy upper leather	: 2 – 4 % HEXATAN SMRP
Garment / upholstery leather	: 2 - 3 % HEXATAN SMRP
Sheep skin	: 2 – 3 % HEXATAN SMRP

The above information has been given in good faith, with out liability





STORAGE

HEXATAN SMRP has a shelf life of one year if stored in its original sealed package. Drums should be tightly resealed each time material is taken from them and their content should be used up as soon as possible after they have been opened.



The above information has been given in good faith, with out liability

