

HEXATAN WL

Replacement liquid syntan based on sulfone

HEXATAN WL

- Especially suitable for the production white leathers including tanning
- Can be used for bleaching chrome and vegetable tanned leather
- Gives fine and uniform milling for natural milled leathers
- Imparts full, fine and smooth grain when applied in re-tanning

PROPERTIES

Appearance	:	Colorless to pale yellow liquid
Chemical Character	:	Condensate of Dihydroxi-diphenyl-sulfone
Solids	:	45 ± 2 %
pH (1:10)	:	3.5 – 4.5
Stability	:	Stable to electrolytes at usual concentrations
Solubility	:	Readily soluble in hot water
Light Fastness	:	Excellent

APPLICATIONS

In Chrome free tanning : 15.0 – 20.0 % **HEXATAN WL**, based on pelt weight

In Re-tanning for : 6.0 – 12.0 % **HEXATAN WL**, based on shaved weight

White leathers

In Re-tanning of : 2.0 – 4.0% **HEXATAN WL**, based on shaved weight

regular process

STORAGE

The product has a shelf life of one year if it is stored in its original sealed packing at temperatures between 5°C and 40°C. Some slight sedimentation may appear if stored for prolonged time under warm conditions. But this does not affect either the solubility or the efficiency of the product. Product Drums should be tightly resealed each time material is taken from them and their content should be used up as soon as possible after they have been opened.

Note: Our range of liquid syntan's has very low electrolyte content, thus low effluent pollution. Also have very less BOD and COD in the effluent. Has an advantage of easy feeding in to drums where the automation methods are adopted.

