

HEXATAN SMA

Styrene maleic copolymer

HEXATAN SMA

- Imparts tight grain with mellow handle
- Keeps softness and body even after wet toggling
- Gives excellent levelling & distribution with selective filling property
- When used after neutralization in re-tanning bath gives mellow handle, while usage after fat liquor and before fixation gives good grain tightening
- Helps in the fixation of dyes and re-tanning agents

PROPERTIES

| | | |
|--------------------|---|--|
| Appearance | : | Yellow to amber liquid |
| Chemical Character | : | Styrene Maleic Copolymer |
| Solids | : | 30 ± 2 % |
| pH (1:10) | : | 8.0-9.0 |
| Stability | : | Not stable to acids |
| Solubility | : | Readily soluble in warm and cold water |
| Light Fastness | : | Excellent |

APPLICATIONS

In Upholstery Leather : 4.0 – 6.0% on shaved weight

In Shoe/ garment : 3.0 – 5.0% on shaved weight

STORAGE

This product has a shelf life of one year if it is stored in its original sealed packing at temperatures between 5°C and 40°C. Drums should be tightly resealed each time material is taken from them and their content should be used up as soon as possible after they have been opened.

