



HEXATAN STR

Soft polymer for pre-tanning and re-tanning

HEXATAN STR

- When used during chrome tanning, will improve the exhaustion and fixation of chrome powder so that we can reduce the quantities of chrome used in the tanning
- In re-tanning with syntans and vegetable extracts it maintains the character of chrome tanning
- Improves the fullness and softness with good touch. Also grain pattern and tightness will be improved
- Can be used alone or in conjunction with other re-tanning agents (vegetable and synthetic)

PROPERTIES

Appearance	:	Colorless to pale yellow viscous liquid
Chemical Character	:	Poly carboxylate
pH (1:10)	:	6.5 - 7.5
Solids	:	30 ± 2 %
Solubility	:	Good
Light fastness	:	Excellent
Stability	:	Stable at all pH values

APPLICATIONS

Pickling : 1.0 - 2.0 % of **HEXATAN STR**

(Based on pelt weight)

Chrome tanning : 2.0 - 3.0 % of **HEXATAN STR** Run 60 'min before the addition of Chrome

Neutralization

(Based on the shaved weight) : 2.0 - 3.0 % of **HEXATAN STR**

Run the drum 20 min before start of neutralization

Re-tanning / fat liquoring : 2.0 - 6.0 % of **HEXATAN STR**

(Based on the shaved weight)

In vegetable / synthetic : 2.0 - 4.0 % of **HEXATAN STR**

(Based on the shaved weight)

In mineral tanning : 2.0 - 4.0 % of **HEXATAN STR**

(Based on the shaved weight)

The above information has been given in good faith, with out liability



STORAGE

This product has a shelf life of one year if it is stored in its original sealed packing at temperatures between 5°C and 40°C. Drums should be tightly resealed each time material is taken from them and their content should be used up as soon as possible after they have been opened.



The above information has been given in good faith, with out liability

