

HEXATAN WR-S

Special re-tanning agent based on Sulphone

HEXATAN WR-S

- Due to high tannin content and no added fillers, leathers produced with **HEXATAN WR-S** will not affect the water repellency and water vapor permeability
- Can be used as pre-tanning agent for the production of wet white leathers, imparts uniform grain tightness including belly portions
- Can be used as high quality synthetic tanning agent for the production of automotive and upholstery leather due to its very low residual monomers
- Gives pleasant handle along with tight and smooth grain
- Excellent buff ability
- Improved dye brilliancy

PROPERTIES

Appearance	:	Off white to cream coloured powder
Chemical Character	:	Condensate of oxy sulphone
Moisture content	:	6.0% Max.
pH (1:10)	:	3.0 – 4.0
Stability	:	Stable to electrolytes at usual concentrations
Solubility	:	Readily soluble in hot water
Light Fastness	:	Excellent

APPLICATIONS

In Chrome free tanning : 6.0 – 10.0 % **HEXATAN WR-S** based on pelt weight.

In Re-tanning for : 4.0 – 10.0% **HEXATAN WR-S** based on shaved weight.

White leathers

In Re-tanning of : 2.0 – 4.0% **HEXATAN WR-S** based on shaved weight.

regular process

STORAGE

The product has a shelf life of two years if it is stored in its tightly sealed original packaging at temperatures between 0°C and 40°C. Bags should be tightly resealed each time material is taken from them, and their contents should be used up as soon as possible after they have been opened.

